

Lip Gloss – “hip.holo.glam”
Ref: CC/3106/EU

Color Cosmetics

Product Name	INCI Name	%W/W	Supplier
A			
Versagel ME 500	Hydrogenated Polyisobutene (and) Ethylene/ Propylene/ Styrene Copolymer (and) Butylene/ Ethylene/ Styrene Copolymer	71.80	www.penreco.com
Silshine 151	Phenylpropyldimethylsiloxysilicate	7.00	www.momentive.com
Silsoft 034	Caprylyl Methicone	7.00	www.momentive.com
Labrafac CC	Caprylic/ Capric Triglyceride	6.00	www.gattefosse.com
B			
MIRAGE Holo Magic	Calcium Sodium Borosilicate (and) Titanium Dioxide (and) Tin Oxide (and) Iron Oxides (and) Silica	8.00	www.eckart.net
C			
Vanilla	Flavor	0.20	www.pura-natura.com

Procedure:

1. Heat phase A to 80-85°C
2. Let batch cool to 75°C and add phase B
3. Add phase C under low shear and mix until homogeneous
4. Fill into an appropriate lip gloss container

⇒ MIRAGE Holo Magic creates a wonderful effect and a nice shine to the lip gloss



Stability:

Stable for at least 6 months at RT and 40°C.
Stable for at least 1 month at 50°C.

Customer Support

ECKART GmbH
info.eckart@altana.com

ECKART America Corporation
info.eckart.cosmetics@altana.com

ECKART Asia Limited
info.eckart.asia@altana.com

This document does not constitute a legally binding obligation of Eckart. While the information contained herein and our technical advice – whether verbal, in writing or by way of trials – are given in good faith, it is provided for your guidance only. We recommend testing our products as to their suitability for your envisaged purpose prior to use. Furthermore, you are responsible for observing all laws and regulations relevant to any products mentioned herein and the products' application. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties.

Date: 20.02.2023
Revision : 20.02.2023